

	Property	Specification (ASTM)	Unit	Material									
				PTFE	PFA	FEP	MFA	THV	ETFE	ECTFE	PVDF	PEEK	
General	Continuous service temperature	Maximum	°C	260	260	200	240	120	150	150	150	250	
			°F	500	500	392	464	250	302	302	302	482	
	Chemical resistance		-	Excellent	Excellent	Excellent	Excellent	Good	Excellent	Good	Good	Excellent	
	Specific gravity	D 792	-	2.15	2.15	2.15	2.15	1.97	1.73	1.70	1.78	1.32	
Electrical	Dielectric constant	D 150 at 10 ³ Hz	-	2.1	2.1	2.1	2.1	3.5	2.6	2.5	7.2	-	
		D 150 at 10 ⁹ Hz	-	2.1	2.1	2.1	2.1	4.2	2.6	2.5	8.5	-	
	Dielectric dissipation factor	D 150 at 10 ³ Hz	-	0.0002	0.0002	0.0001	0.0002	0.12	0.0008	0.0018	0.030	-	
		D 150 at 10 ⁵ Hz	-	0.0002	0.0003	0.0008	0.0003	0.17	0.005	0.0012	9 x 10 ⁻²	-	
	Dielectric strength (short term) 10 mils film	D 149	Volt/mil	> 1 400	2 000	2 000	2 000	1 8	2 000	2 000	1 600	>500	
Volume resistivity	D 257	Ohm·cm	>10 ¹⁸	>10 ¹⁸	>10 ¹⁸	>10 ¹⁷	>10 ¹⁵	>10 ¹⁵	>10 ¹⁵	>10 ¹⁴	>10 ¹⁶		
Environmental	Water absorption	D 570	%	< 0.01	< 0.03	< 0.01	< 0.03	< 0.01	< 0.03	< 0.01	< 0.04	< 0.5	
	Weather resistance	-	-	Excellent	Excellent								
	Oxygene index	D 2863	%	> 95	> 95	> 95	> 95	> 65	> 30	60	44	35	
	Flammability	UL 94	-	V-0	V-0								
Mechanical	Tensile strength	D 1708, D 638	psi	3 500	4 000	3 500	3 500	4 300	6 500	7 000	5 000	2 100	
	Elongation	D 1708, D 638	%	300	300	300	300	500	200	200	150	50	
	Compressive strength	D 695	psi	3 500	2 200	2 200	2 200	1 800	7 000	7 000	11 600	17 100	
	Impact strength	D 256 at +23°C	Ft-Lb/in	3.5	No Break	3-6	655						
	Flexural Modulus	D 790 at +23°C	psi	90 000	100 000	95 000	95 000	180 000	200 000	240 000	250 000	530 000	
	Tensile Modulus	D 638	psi	80 000	40 000	50 000	40 000	30 000	120 000	240 000	200 000	520 000	
	Hardness	D 2240	-	D-60	D-60	D-55	D-59	D-45	D-75	D-75	D-78	R-126	
Thermal	Melting point		°C	327	305	270	285	125-185	260° C	240	160	334	
			°F	620	581	518	545	257-365	500° F	464	320	633	
	Thermal conductivity	C-177	BTU/hr/ft ² /°F·in	1.7	1.3	1.4	1.4	1.4	1.6	1.6	1.3	1.2	
	Deflection temperature 66 psi 264 psi	D 648	°C	122	74	59	65	31-37	104	104			
				55	48	57	50	28-32	71	71	113	141	
Deflection temperature 66 psi 264 psi	D 648	°F	252	166	138	149	88-99	220	220				
			131	118	134	122	82-90	160	160	235	285		

*We do not guarantee the accuracy of the technical information and reserve the right to make changes without prior notice. The information is provided without warranty and does not imply any liability.